



# TECHNICAL DATA SHEET

**TREMPRO® 635**  
Fast-Cure, Low VOC, High Solids  
Polyurethane Sealant

---

## PRODUCT DESCRIPTION

TREMPRO® 635 utilizes a solvent-free technology, which represents technical advances over existing polyurethane systems. In addition, TREMPRO 635 demonstrates excellent adhesion to a wide variety of substrates, including ferrous, non-ferrous metals, kynar finishes, composite materials and many plastic rubber substrates.

TREMPRO 635 is a high performance, low-to-medium modulus, onecomponent, gun grade polyurethane sealant. The sealant cures to a flexible rubber when exposed to atmospheric moisture.

---

## BASIC USES

TREMPRO 635 is specially designed for use as a topical sealant in the fabrication of trailers, trucks, campers, buses, trains and specialty vehicles. It can also be used in joints and seams in architectural panels and preengineered buildings.

---

## FEATURES & BENEFITS

- TREMPRO 635 demonstrates excellent physical properties regarding adhesion, vibration, movement, shear strength and weatherability.
- TREMPRO 635 can easily be applied to butt and fillet joint applications.

---

## PACKAGING

10.1-oz (300-mL) cartridges, 10- and 20-oz (300- and 600-mL) sausages, 5gal (19-L) pails, or 55-gal (208-L) drums.

---

## COLORS

Gray and White.

---

## AVAILABILITY

Immediately available from your local Tremco Field Representative, Tremco Distributor or Tremco Warehouse.

---

## LIMITATIONS

- Do not apply over damp or contaminated surfaces.

---

## SUBSTRATE PREPARATION

For good adhesion, the joint surface must be sound, clean and dry. Depending on the substrate, the joint surface may require a thorough wire brushing with steel wool or Scotch-Brite pad and/ or solvent wipe.

---

## SUBSTRATE PREPARATION

TREMPRO 635 is applied with conventional caulking equipment. Fill joint or seam completely and tool. At 75 °F (23.9 °C), 50% RH, a durable skin forms within hours after application.

Damaged Sealant can be repaired. Consult Tremco Technical Services or a Sales Representative for repair procedures.

---

## CLEAN UP

Tooling is recommended immediately after application to ensure firm, intimate contact with the joint interface. Dry tooling is preferred. Excess sealant and smears adjacent to the joint can be removed with Xylol or Toluol before sealant cures.

---

## WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

### TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL RESULTS
Extrusion Rate		20 to 30 seconds
Percent Elongation		400 to 600%
Shore A Hardness	ASTM C661	22 to 32
Skin Formation		40 to 60 minutes (typical)
Tensile Strength		250 to 350 psi

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

**NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.**

TP635-DS/1222



Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



[tremcosealants.com](http://tremcosealants.com) | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122  
800.321.7906 | [tremcocpg.com](http://tremcocpg.com)